

AMENDMENT TO THE CLAIMS

1. (currently amended) A head for a magnetic drive, comprising:
a substrate with a thermal expansion rate CTE1;
a transducer that has a bond to the substrate and that has a
transducer thermal expansion rate CTE2 that is greater
than CTE1, the transducer having two opposite sides;
and
a first restraint layer that has a bond to a first one of
the sides of the transducer and that has a first
restraint layer thermal expansion rate CTE3 that is
less than CTE1, the first restraint layer having a
combination of a Young's Modulus, a Poisson's ratio and
a thickness such that the first restraint layer pulls
the transducer back away from magnetic media to avoid
contact with magnetic media at high head temperatures.

2. (original) The head of Claim 1 wherein the transducer and the
first restraint layer are bonded together to have a combined
expansion rate that is substantially matched with CTE1.

3. (original) The head of Claim 1, wherein the first restraint
layer has dimensions and material properties that are selected to
limit protrusion of the transducer beyond the substrate over an
operating temperature range.

4. (original) The head of Claim 1, further comprising:
a second restraint layer that has a bond to a second one of
the sides of the transducer, and that has an second
restraint layer thermal expansion rate CTE4 that is
less than CTE1.

5. (original) The head of Claim 4 wherein the transducer and the
first and second restraint layers are bonded together to have a

Cl
ent

combined expansion rate that is substantially matched with CTE1.

6. (original) The head of Claim 5, further comprising a third layer that has a bond to the second restraint layer.

7. (original) The head of Claim 6, further comprising a bonding film between the second restraint layer and the third layer.

8. (original) The head of Claim 1 wherein the first restraint layer has a restraint layer width that is substantially the width of the transducer.

9. (original) The head of Claim 1 wherein the first restraint layer has a restraint layer width that is substantially the width of the substrate.

Cl
CMT
10. (original) The head of Claim 1 wherein the substrate comprises ceramic material with a thermal expansion rate in the range of about $7 \times 10^{-6} / ^\circ\text{C}$. to $8.3 \times 10^{-6} / ^\circ\text{C}$.

11. (original) The head of Claim 10 wherein the transducer comprises metals with thermal expansion rates in the range of $12 \times 10^{-6} / ^\circ\text{C}$ to $17 \times 10^{-6} / ^\circ\text{C}$.

12. (original) The head of Claim 11 wherein the first restraint layer comprises material with a thermal expansion rate of about $1 \times 10^{-6} / ^\circ\text{C}$ to $4.3 \times 10^{-6} / ^\circ\text{C}$ selected from the group: aluminum nitride, silicon nitride and silicon dioxide.

13. (currently amended) A method of manufacturing a head for a magnetic drive, comprising:

- A. providing a substrate with a thermal expansion rate CTE1;
- B. bonding a transducer with a thermal expansion rate CTE2

greater than CTE1 to the substrate, the transducer having two opposite sides;

- C. bonding a first restraint layer to a first one of the sides of the transducer, the first restraint layer having a thermal expansion rate CTE3 less than CTE1; and
- D. effectively compensating for thermal expansion of the substrate and the transducer by setting a combination of a Young's Modulus, a Poisson's ratio and a thickness of the first restraint layer such that the first restraint layer pulls the transducer back away from magnetic media to avoid contact with magnetic media at high head temperatures.

14. (original) The method of Claim 13 further comprising:

- D. bonding the transducer and the first restraint layer together to have a combined expansion rate that is substantially matched with CTE1.

15. (original) The method of Claim 13 further comprising:

- D. selecting dimensions and material properties for the first restraint layer to limit protrusion of the transducer beyond the substrate over an operating temperature range.

16. (original) The method of Claim 13, further comprising:

- D. bonding a second restraint layer to a second one of the sides of the transducer, the second restraint layer having a thermal expansion rate CTE4 that is less than CTE1.

17. (original) The method of Claim 13 further comprising:

- D. including a material in the first restraint layer

selected from the group: aluminum nitride, Si_3N_4 and SiO_2 .

18. (original) The method of Claim 13, further comprising:
D. forming the first restraint layer by thin film deposition.

19. (currently amended) A head for a magnetic drive, comprising:
a head assembly including a substrate and a magnetic transducer; and
means for restraining thermal expansion of the magnetic transducer, wherein the means for restraining has a combination of a Young's Modulus, a Poisson's ratio and a thickness such that the means for restraining pulls the transducer back away from magnetic media to avoid contact with magnetic media at high head temperatures.

C1
amended